

## AF1601 Data Sheet F109-BR85 (Genuine VITON\*) FPM F109 – Brown (Bisphenol Cross Linked)

### General

F109-BR85 is a brown Fluorocarbon elastomer, commonly referred to as VITON\* and FPM. FPM materials have a very high resistance to hydraulic fluids, chemicals and a number of organic compounds and operate in temperatures between -20 to +210°C. F109-BR85 is recommended for applications where its outstanding resistance to heat, chemicals, weathering and ozone is required.

### Physical properties

Density	DIN 53479	g/cm <sup>3</sup>	2,44
Hardness at 20°	DIN 53505	Shore A	85 +/-5
Tensile strength	DIN 53504	N/mm <sup>2</sup>	11,7 +/-15%
Elongation at break	DIN 53504	%	154 +/-20%
Modulus 100%	DIN 53504	N/mm	8,8 +/-30%
Tear strength	DIN 53507B	N/mm	4,2
Compression set: 70h/RT	DIN 53517A	%	14,1 +/-20%
Compression set: 22h/70°C	DIN 53517A	%	9,4 +/-25%
Compression set: 22h/100°C	DIN 53517A	%	6,0 +/-25%
Compression set: 24h/175°C	DIN 53517	%	9,4 +/-25%
Min. service temperature		°C	-20
Max. service temperature		°C	210
Short time max. service temp. in air		°C	280

### Chemical resistance

Water up to 90°	S	Biodegradable oils	R
Steam	U	Hydrocarbons	R
HFA, HFB, HFC fluids	S	Alcohols	U
HFD-S, R	R	Diesel, gasoline, fuels	R
Mineral oils	R	Ozone, oxygen	R
Vegetable oils	R	Air up to 200°	R
Silicone oils	R		

Key to chemical resistance: R = Resistant S = Suitable U = Unsuitable

### Main application

Static and dynamic seals (standard and special), wipers, O-rings, flange seals, rotary seals, rubber energisers (preload elements). Applications where high temp. and/or chemical resistance is required.

### Analysis and evaluation

The mentioned properties are only valid for test pieces of the corresponding ISO, DIN and ASTM standards. They cannot be directly related to seals, gaskets and other sealing products and should be used only as a general guide.

\*VITON is a registered Trademark of Du Pont Co./USA.

Issued July 2013 AFT Fluorotec Technical Department.

All information is based on typical test results performed under specific conditions and limited sample size. This does not represent a legally binding guarantee of certain properties or the suitability for specific applications.

### AFT Fluorotec

Solutions and components in Fluoropolymer Plastics

**Phone:** +44 (0) 1992 515880  
**Fax:** +44 (0) 1992 554490  
**Email:** info@fluorotec.com  
**Website:** www.fluorotec.com

Unit 2, Pages Old Mill  
Tamworth Road  
Hertford  
Herts. SG13 7DG